

## Natural Hydraulic Lime NHL 2

Chemical Analysis (Dry Basis)		Typical % Mass	Specification % Mass
Calcium hydroxide	Ca(OH) <sub>2</sub>	78.0	
Calcium carbonate	CaCO <sub>3</sub>	3.0	
Silica	SiO <sub>2</sub>	5.08	
Calcium trialuminate	C3A	0	
Aluminium oxide	Al <sub>2</sub> O <sub>3</sub>	1.42	
Ferric oxide	Fe <sub>2</sub> O <sub>3</sub>	0.65	
Sulfate	SO <sub>3</sub>		3.0 max.
Available lime		59.10	15.0 min.
Physical Analysis			
	(Microns)	Passing %	
Particle Size	200		95.0 % min.
	180	100.00	
	90	99.98	85.0 % min.
28 Day strength test	N/mm <sup>2</sup> (MPa)	2.0 - 3.0	≥ 2 and ≤ 7 MPa
60 Day strength test	N/mm <sup>2</sup> (MPa)	2.5 - 3.5	
90 Day strength test	N/mm <sup>2</sup> (MPa)	3.0 - 4.0	
Bulk Densities	Compacted kg/m <sup>3</sup>	475	

This specification relates to product numbers: **PS170001 - Bulk or Bags**

Revision: 2 Date: 12-June-08

**Storage** Recommended minimum bulk silo capacity for quicklime/Aqualime® 60m<sup>3</sup>, Ultralime® 120m<sup>3</sup>.  
Further advice/information available on request.

**Safety** Refer to our Safety Data Sheet. [Sales: Mike Wye & Associates Ltd. www.mikewye.co.uk, sales@mikewye.co.uk, 01409-281644](mailto:Sales@MikeWye.com)

The information contained in this data is, to the best of our knowledge, true and accurate, but any typical values given are subject to variation as the raw material is naturally occurring. Full test method details available on request.